



FYTISA
Filtros y tejidos
industriales, S.L.

Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	Texfel Style 140
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	Various colours
Uso / <i>Use</i> :	Embroidery, Decoration, Handicraft,...
Fecha / <i>Date</i> :	January 2004

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	140 ± 10%	g/m ²	
THICKNESS	ISO 9073-2	1,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	2	m	
ROLL LENGTH	Countmeter	30	m	



FYTISA
Filtros y tejidos
industriales, S.L.

Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	Texfel Style 200
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	Various colours
Uso / <i>Use</i> :	Embroidery, Decoration, Handicraft,...
Fecha / <i>Date</i> :	February 2009

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	200 ± 10%	g/m ²	
THICKNESS	ISO 9073-2	1,50 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	2	m	
ROLL LENGTH	Countmeter	30	m	



FYTISA
Filtros y tejidos
industriales, S.L.

Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	Texfel Style 500
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	Various colours
Uso / <i>Use</i> :	Embroidery, Decoration, Handicraft,...
Fecha / <i>Date</i> :	September 2010

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	500 ± 10%	g/m ²	
THICKNESS	ISO 9073-2	3,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	1	m	
ROLL LENGTH	Countmeter	20	m	



FYTISA
Filtros y tejidos
industriales, S.L.

Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	Texfel Style 800
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	Various colours
Uso / <i>Use</i> :	Embroidery, Decoration, Handicraft,...
Fecha / <i>Date</i> :	April 2013

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	800 ± 10%	g/m ²	
THICKNESS	ISO 9073-2	5,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	0,90 / 1,80	m	
ROLL LENGTH	Countmeter	15	m	