



**FYTISA**  
Filtros y tejidos  
industriales, S.L.

## Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	<b>Texfel Style 100</b>
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	<b>Various colours</b>
Uso / <i>Use</i> :	<b>Embroidery, Decoration, Handicraft,...</b>
Fecha / <i>Date</i> :	<b>September 2010</b>

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	100 ± 10%	g/m <sup>2</sup>	
THICKNESS	ISO 9073-2	0,60 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
WIDTH	Tape measure	1,5	m	
ROLL LENGTH	Countmeter	50	m	



**FYTISA**  
Filtros y tejidos  
industriales, S.L.

## Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	<b>Texfel Style 140</b>
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	<b>Various colours</b>
Uso / <i>Use</i> :	<b>Embroidery, Decoration, Handicraft,...</b>
Fecha / <i>Date</i> :	<b>January 2004</b>

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	140 ± 10%	g/m <sup>2</sup>	
THICKNESS	ISO 9073-2	1,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	2	m	
ROLL LENGTH	Countmeter	30	m	



**FYTISA**  
Filtros y tejidos  
industriales, S.L.

## Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	<b>Texfel Style 200</b>
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	<b>Various colours</b>
Uso / <i>Use</i> :	<b>Embroidery, Decoration, Handicraft,...</b>
Fecha / <i>Date</i> :	<b>February 2009</b>

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	200 ± 10%	g/m <sup>2</sup>	
THICKNESS	ISO 9073-2	1,50 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	2	m	
ROLL LENGTH	Countmeter	30	m	



**FYTISA**  
Filtros y tejidos  
industriales, S.L.

## Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	<b>Texfel Style 500</b>
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	<b>Various colours</b>
Uso / <i>Use</i> :	<b>Embroidery, Decoration, Handicraft,...</b>
Fecha / <i>Date</i> :	<b>September 2010</b>

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	500 ± 10%	g/m <sup>2</sup>	
THICKNESS	ISO 9073-2	3,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	1	m	
ROLL LENGTH	Countmeter	20	m	



**FYTISA**  
Filtros y tejidos  
industriales, S.L.

## Ficha Técnica Technical Data Sheet

Familia Producto / <i>Product Family</i> :	<b>Texfel Style 800</b>
Calidad / <i>Material</i> :	-
Acabado / <i>Finish - Front Side</i> :	-
Acabado / <i>Finish - Back Side</i> :	-
Color / <i>Colour</i> :	<b>Various colours</b>
Uso / <i>Use</i> :	<b>Embroidery, Decoration, Handicraft,...</b>
Fecha / <i>Date</i> :	<b>April 2013</b>

FEATURE	TEST METHOD	SPECIFIED VALUE	UNIT	REMARKS
FIBER COMPOSITION		100% PES		
STRUCTURE OF THE SURFACE	Visual	According to the released sample		
WEIGHT	ISO 9073-1	800 ± 10%	g/m <sup>2</sup>	
THICKNESS	ISO 9073-2	5,00 ± 10%	mm	
COLOUR FASTNESS				
TO COMMERCIAL & DOMESTIC LAUNDERING	ISO 105-C06	4 - 5	GS	Grey Scale
TO RUBBING	ISO 105-X12		GS	Grey Scale
Dry		4 - 5		
Damp		4 - 5		
TO IRONING	ISO 105-X11		GS	Grey Scale
Dry		5		
Damp		4 - 5		
Wet		4 - 5		
TO ORGANIC SOLVENTS	ISO 105-X05	4 - 5	GS	Grey Scale
TO ARTIFICIAL LIGHT	ISO 105-B02	6	BS	Blue Scale
DIMENSIONAL STABILITY	(60°C)	Max. 1%	%	
WIDTH	Tape measure	0,90 / 1,80	m	
ROLL LENGTH	Countmeter	15	m	